

⑫

EUROPEAN PATENT APPLICATION

⑰ Application number: 88301308.8

⑥ Int. Cl.⁴: **A 61 K 7/00**
B 01 F 11/02

⑱ Date of filing: 17.02.88

③① Priority: 19.02.87 US 16600

④③ Date of publication of application:
24.08.88 Bulletin 88/34

⑥④ Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI NL SE

⑦① Applicant: UNILEVER PLC
Unilever House Blackfriars P.O. Box 68
London EC4P 4BQ (GB)

⑥④ Designated Contracting States: GB

⑦① Applicant: UNILEVER NV
Burgemeester s'Jacobplein 1 P.O. Box 760
NL-3000 DK Rotterdam (NL)

⑥④ Designated Contracting States:
BE CH DE ES FR GR IT LI NL SE AT

⑦② Inventor: Vishnupad, Mohan
130 Knorr Road
Monroe Connecticut 06468 (US)

Ramirez, Jose E.
15 Fox Court
Trumbull Connecticut 06468 (US)

Bornfriend, Robert A.
14 Sophia Drive
Ridgefield Connecticut 06877 (US)

⑦④ Representative: Tonge, Robert James et al
UNILEVER PLC Patents Division P.O. Box 68 Unilever
House
London EC4P 4BQ (GB)

⑤④ Cosmetic compositions.

⑤⑦ A stable, water dispersible petroleum jelly formulation, which is an oil-in-water emulsion, is described which comprises water, petroleum jelly, optional humectant, and emulsifier. The composition is formed by ultrasonically emulsifying the various components which will ultimately form the emulsion.

Description

COSMETIC COMPOSITIONSBACKGROUND OF THE PRESENT INVENTIONField of the Invention

The present invention relates to petroleum jelly compositions (oil-in-water emulsions) which are easily dispersible in water.

Description of the Prior Art

It is taught in U.S. Patent No. 3,852,475 that the inclusion of hydrophobic starch in topical compositions containing solid petroleum jelly reduces the greasy appearance and feel normally associated with such compositions as well as reducing the resistance of the compositions to washing with cold water soap and detergent compositions. The compositions that are shown in this patent contain no aqueous phase, are not emulsions, and are, moreover, apparently not dispersible in water. Similarly, U.S. Patent No. 4,035,514 indicates that petroleum jelly containing up to 30%, by weight, of a combination dispersing agent comprising cetyl alcohol, lanolin alcohols and alkoxylated fatty acid esters of sorbitol can be dispersed in water without the use of additional soaps or detergents. Once again, this reference relates to petroleum jelly compositions which do not contain a water phase since they are described as viscous salves or creams. The compositions shown in this patent are merely designed to be dispersed in water and consist of an oil phase in combination with the dispersing agent only.

Cosmetic and Toiletry Formulations by E. W. Flick, on page 225, illustrates a cream comprising petrolatum, emulsifier, and water which is characterized as "oily" and "not dispersible in water".

Drug and Cosmetic Industry, Vol. 94, No. 6, June 1964, pages 821-824 and 920 mentions use of an ultrasonic emulsifier to produce a product called "Dry Skin Cream" (for Chesebrough-Pond's Inc.) which differs from the types of compositions which are part of the present invention in the following major ways: The resulting composition was a non-stable water-in-oil emulsion (rather than an oil-in-water emulsion) containing very low amounts (e.g., about 10% or so) of petroleum jelly; and, if added to water, such a composition would not readily disperse to form a milky white composition containing petroleum jelly of micron and submicron size.

SUMMARY OF THE PRESENT INVENTION

The present invention is a stable, readily water dispersible petroleum jelly oil-in-water emulsion which comprises water, petroleum jelly, humectant (as an optional, but preferred ingredient), and emulsifier. The emulsion is made and is made stable by processing the various ingredients forming it through an ultrasonic emulsifier. The particle size of the oil phase in the present emulsions is predominantly of micron and submicron size.

The compositions of the present invention are oil-in-water emulsions which are stable (i.e., do not separate upon standing) and which are readily water dispersible in water. The term "water dispersible" as used herein is intended to indicate that when these emulsions are added to a larger volume of water, they form a milky white, substantially uniform dispersion of petroleum jelly particles of micron (e.g., up to only a few microns) and submicron size in the water upon being mixed therein. The instant emulsions, in preferred embodiments, can contain relatively high levels of petroleum jelly (e.g., about 30-about 60%, by weight).

DETAILED DESCRIPTION OF THE PRESENT INVENTION

The oil phase of the compositions of the present invention comprise petroleum jelly either in neat or modified form. Modified forms of petroleum jelly include these compositions where some of the petroleum jelly has been replaced by mineral oil. The petroleum jelly that is intended for use in a preferred embodiment is a purified mixture of semi-solid hydrocarbons obtained from petroleum, chiefly of the methane series having a white to faintly yellowish color, a density of from about 0.820-0.865, a melting point of from about 38-54°C and a refractive index of 1.460-1.474. The amount of the oil phase in the present emulsions can range anywhere from about 15% to about 70%, by weight, of the total weight of the emulsion of the present invention. The amount of petroleum jelly can range from about 30% to about 60%, by weight, for example, in preferred embodiments.

The aqueous phase of the present invention comprises water, an optional but preferred humectant, and an oil-in-water emulsifier which is effective to confer the water dispersible characteristics on the composition of the present invention as essential ingredients. Generally speaking the weight percentage of the aqueous phase can range anywhere from about 30% to about 85%, by weight, of the entire emulsion.

The amount of water which can be contained in the aqueous phase of the emulsions of the present invention can range from about 30% to about 85%, by weight, of the aqueous phase.

The optional, though preferred, humectant which can be present in the aqueous phase of the emulsion of the present invention are those which are generally used in skin care products. The humectant can be present from about 0% to about 90%, by weight, of the aqueous phase. Examples of suitable humectants include glycerine, propylene glycol, sorbitol, sucrose, and the alkali metal salts of pyrrolidone carboxylic acid.

The oil-in-water emulsifying agent which is an essential component of the present invention should be

present at from about 2% to about 6%, by weight, of the aqueous phase. Representative, compatible emulsifying agents that can be utilized include the dialkanolamine alkyl phosphate emulsifiers such as the diethanolamine monoalkyl phosphate species which are complex mixtures of esters of phosphoric acid and long chain alkyl groups. A commercially available material of this type is available under the trademark AMPHISOL and is a complex alkyl phosphate of diethanolamine carrying CAS Registry No. 69331-39-1.

In accordance with the present invention it has been found necessary that the aforementioned components which make up the emulsion be processed through an ultrasonic emulsifier in order to insure production of a stable emulsion. Conventional emulsifying apparatus such as colloid mills and homomixers do not produce stable emulsions in accordance with the present invention. Generally speaking, the size of the petroleum jelly or modified petroleum jelly component in the continuous water phase should range anywhere from about 15% to about 70% in preferred embodiments. Appropriate ultrasonic emulsifier apparatus which can be used to make the emulsions of the present invention are known to persons of ordinary skill in the art. A preferred type of apparatus is available under the trademark SONOLATOR from Sonic Corp., Stratford, CT.

U.S. Patent Nos. 3,926,413 and 3,176,964, both of which are incorporated herein by reference, illustrate the general construction details of the SONOLATOR apparatus. Stated simply, such an apparatus operates by the feeding (≥ 200 lbs. force/in²), through a jet into a cavitation zone in the form of a thin flat liquid stream at velocities of ≥ 200 ft./sec, where it impinges onto a fixed blade and forces the blade to resonate at its natural, ultrasonic, resonant frequency. Cavitation is induced along the leading edge of the blade and the shock waves caused by the collapse of the cavitation bubbles shatter the large liquid globules and produce fine homogenization.

A suitable generalized and preferred manufacturing procedure for the compositions of the present invention is as follows:

Oil Phase Preparation

1. Petroleum jelly and glyceryl monostearate are heated (e.g., to 70°C).
2. Propyl paraben is melted into the resulting oil phase.
3. The diethanolamine monoalkyl phosphate emulsifier is then added, and the resulting compositions is mixed until uniform.
4. Oil soluble humectant(s) are then added and mixture is resumed.

Water Phase Preparation

1. Water is heated to 70°C.
2. The water soluble ingredients are dissolved in the heated water and mixing is resumed.

After the above preparation of the respective water and oil phases, they are combined and processed in the following manner:

1. The water phase is added to the oil phase and is mixed until uniform, keeping the mixture hot (e.g., 70°C).
2. The resulting mixture is passed once (or multiple times) through the ultrasonic emulsifier (SONOLATOR emulsifier apparatus) at sufficient pressure (e.g., 1500 psi) to give the desired viscosity.
3. The resulting emulsion is collected in a kettle, cooled (e.g., to 60°C) and fragrance is then added.

The emulsions which are the subject of the present specification and claims are of the oil-in-water type and are readily dispersible in water. Their pH ranges from about 5.4 to 5.8 with the following typical preferred viscosity ranges depending upon the power and number of cycles of the compositions through the SONOLATOR apparatus:

Initial (at room temperature)

- 1 cycle : 975 - 2000 cps
- 2 cycles: 1000 - 3000 cps
- 3 cycles: 1700 - 3000 cps

The compositions, in general, can have viscosities of from about 900 to about 3000 cps.

The Examples which follow set forth certain specific embodiments of the present invention.

EXAMPLE 1

The following ingredients were used to make a water dispersible petroleum jelly oil-in-water emulsion:

	<u>Incredient</u>	<u>Weight Percent</u>
	Petroleum jelly	50.00
5	Diethanolamine monoalkyl phosphate (AMPHISOL)	3.00
	Glyceryl monostearate	2.00
10	Propyl paraben	0.10
	Methyl paraben	0.15
	Deionized water	34.25
15	Propylene glycol	10.00
	Bath oil fragrance	0.50

20 The petroleum jelly and glyceryl monostearate were heated to 70°C forming an oil phase mixture to which was then added the propyl paraben and diethanolamine monoalkyl phosphate (AMPHISOL). The resulting oil phase mixture was mixed until uniform.

The water was heated to 70°C and the methyl paraben was dissolved therein. The propylene glycol was added to the resulting aqueous mixture and mixed into it forming an aqueous phase mixture.

25 The water phase mixture was added to the oil phase mixture and mixed for 20 minutes. The fragrance was added at 60°C. The resulting mixture was passed through an ultrasonic emulsifier (SONOLATOR brand) at 60°C with a setting of 1500 psi on the emulsifier to yield a stable emulsion. It has been found that the use of temperatures below about 60°C and the use of feed pressures of lower than 1500 psi in the apparatus utilized in this Example tended to produce unstable emulsions.

30 Emulsion stability can be further improved by passing the emulsion through the ultrasonic emulsifier more than once. The repeated emulsification produces higher viscosity emulsions without any substantial change in the water dispersible characteristics of the product.

The data given below reports the results of treating the composition of this Example to a variety of passes through the apparatus:

	<u>No. of Passes</u>	<u>Initial Viscosity at 25°C</u> <u>(cps units)</u>
40	1	1340
	2	2080
	4	3200
45	6	3910

EXAMPLE 2

50 The following examples were used to make another oil-in-water emulsion using the same general procedure described in Example 1.

55

60

65

<u>Ingredient</u>	<u>Weight Percent</u>	
Petroleum jelly	48.00	
Diethanolamine monoalkyl phosphate (AMPHISOL)	3.00	5
Glyceryl monostearate	2.00	10
Propyl paraben	0.10	
Methyl paraben	0.15	15
Water	34.25	
Acetylated lanolin alcohol (ACETULAN)*	2.00	20
Propylene glycol	10.00	
Bath oil fragrance	0.50	25
*heated with the petroleum jelly and glyceryl monostearate initially.		30

The above composition was subjected to ultrasonic emulsification under varying conditions:

A: One pass at 164°F giving a composition having an initial viscosity of 225 cps. The overnight viscosity was 1630 cps and the overnight pH was 5.68.

B: One pass at 164°F and one pass at 140°F gave a composition having an initial viscosity of 875 cps. The overnight viscosity was 3610 cps and the overnight pH was 5.70.

C: One pass at 164°F and three passes at 140°F gave an initial viscosity of 1700 cps. The overnight viscosity was 5900 cps and the overnight pH was 5.60.

D: One pass at 164°F and five passes at 148°F produced an initial viscosity of 1300 cps. The overnight viscosity was 6600 cps and the overnight pH was 5.60.

The emulsions were acceptable and were easily dispersible in water.

EXAMPLE 3

The following formulation was made as previously described:

	<u>Ingredient</u>	<u>Weight Percent</u>
5	Petroleum jelly	50.00
	Diethanolamine monoalkyl phosphate (AMPHISOL)	3.00
10	Glyceryl monostearate	2.00
	Propyl paraben	0.10
	Methyl paraben	0.15
15	Water	34.05
	Xanthan gum (KELTROL)*	0.20
	Propylene glycol	10.00
20	Fragrance	0.50

25 *mixed with the heated water prior to addition of the methyl paraben.

The resulting mixture was subjected to ultrasonic emulsification:

30	<u>A:</u>	Passes:	1 at 160°F
		Initial Viscosity:	1700 cps
		Overnight Viscosity:	5000 cps
35		Overnight pH:	5.73
	<u>B:</u>	Passes:	2 at 140°F
		Initial Viscosity:	2900 cps
40		Overnight Viscosity:	7150 cps
		Overnight pH:	5.75
	<u>C:</u>	Passes:	4 at 144°F
		Initial Viscosity:	2900
45		Overnight Viscosity:	8280 cps
		Overnight pH:	5.77

50 The emulsions were acceptable and were easily dispersible in water.

The foregoing Examples are intended to illustrate certain preferred embodiments of the present invention but should not be construed in a limiting sense. The scope of protection that is sought is set forth in the claims which follow.

55

Claims

- 60 1. An ultrasonically emulsified stable, water-dispersible oil-in-water emulsion, which comprises:
- (i) from 15 to 70% by weight of an oil phase, and
 - (ii) from 30 to 85% by weight of an aqueous phase,
- the emulsion being further characterised by comprising:
- (a) from 15 to 75% by weight of petroleum jelly, and
 - (b) from 2 to 6% by weight of emulsifier.
- 65 2. A emulsion according to claim 1, in which water forms from 30 to 85% by weight of the aqueous phase.

3. An emulsion according to claim 1 or 2, in which the emulsifier is a dialkanolamine alkyl phosphate emulsifier.

4. An emulsion according to claim 3, in which the emulsifier is diethanolamine monoalkyl phosphate.

5. An emulsion according to any preceding claim, which additionally comprises from 0 to 90% by weight of the aqueous phase of a humectant.

6. An emulsion according to any preceding claim, which additionally comprises a fragrance.

7. A method of forming a stable, water-dispersible oil-in-water emulsion according to any preceding claim, which comprises the step of ultrasonically emulsifying a mixture of water, petroleum jelly and emulsifier.

8. A method according to claim 7 which comprises the steps of:

(i) preparing an oil phase by heating together a mixture of petroleum jelly, emulsifier and other optional oil-soluble ingredients,

(ii) preparing an aqueous phase by heating water together with optional water-soluble ingredients,

(iii) adding the heated aqueous phase to the heated oil phase,

(iv) passing the mixture so formed at least once through an ultrasonic emulsifier, and

(v) optionally adding fragrance to the ultrasonically emulsified emulsion so obtained.

THIS PAGE BLANK (USPTO)

THIS PAGE BLANK (USPTO)

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 279 641
A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 88301308.8

(51) Int. Cl.⁵ A61K 7/00, B01F 11/02

(22) Date of filing: 17.02.88

(30) Priority: 19.02.87 US 16600

(43) Date of publication of application:
24.08.88 Bulletin 88/34(84) Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI NL SE(88) Date of deferred publication of the search report:
16.05.90 Bulletin 90/20(71) Applicant: UNILEVER PLC
Unilever House Blackfriars P.O. Box 68
London EC4P 4BQ(GB)

(84) GB

Applicant: UNILEVER NV
Burgemeester s'Jacobplein 1 P.O. Box 760
NL-3000 DK Rotterdam(NL)

(84) BE CH DE ES FR GR IT LI NL SE AT

(72) Inventor: Vishnupad, Mohan
130 Knorr Road
Monroe Connecticut 06468(US)
Inventor: Raminez, Jose E.
15 Fox Court
Trumbull Connecticut 06468(US)
Inventor: Bornfriend, Robert A.
14 Sophia Drive
Ridgefield Connecticut 06877(US)(74) Representative: Tonge, Robert James et al
UNILEVER PLC Patents Division P.O. Box 68
Unilever House
London EC4P 4BQ(GB)

(54) Cosmetic compositions.

(57) A stable, water dispersible petroleum jelly formulation, which is an oil-in-water emulsion, is described which comprises water, petroleum jelly, optional humectant, and emulsifier. The composition is formed by ultrasonically emulsifying the various components which will ultimately form the emulsion.

EP 0 279 641 A3



EP 88 30 1308

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
A	PHARMACEUTICA ACTA HELVETIAE, vol. 47, no. 8-9, 1972, pages 516-536; M. SEILLER et al.: "Emulsions" * Pages 516-536 * ---	1,7-8	A 61 K 7/00 B 01 F 11/02
A	EP-A-0 166 946 (SCHERING WIEN) * Page 9, paragraph 1: "Herstellung der Öl/Wasser-Emulsion"; claims * ---	1-2,5,6	
A	CHEMICAL ABSTRACTS, vol. 97, no. 10, September 1982, page 423, abstract no. 78917b, Columbus, Ohio, US; & JP-A-82 93 906 (LION CORP.) 11-06-1982 ---	1-2,5,6	
A	US-A-4 542 745 (OAKLEY et al.) * Whole document * -----	1,7-8	
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			A 61 K
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 05-02-1990	Examiner FISCHER J.P.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			